

# Armada®

## Tight Buffered Distribution Fibre Optic Cable

### HFFR SHF-1



## Cable Design

Fibre Type	Tight Buffered colour coded optical fibres
Strength member	Glass fibre yarns (swellable for longitudinal watertightness and as rodent protection)
Inner Jacket	FR-LSZH FireFighter UV-Stabilised, Black
Armour	DataGuard Galvanised steel wire braid (GSWB)
Outer Jacket:	FR-LSZH FireFighter SHF-1, UV-Stabilised Black

## Mechanical & Thermal Characteristics

Crush resistance		2000 N/10cm
Impact resistance		3 impacts (w/20N.m)
Bending Radius (min.)	Static	15 x Ø
	Dynamic	20 x Ø
Compound Flow		30 cm/24h/70°C passed
Temperature range	Storage	-40°C to +60°C
	Installation	-5°C to +40°C
	Operating	-20°C to +50°C

## Fire Behaviour

Flame Retardant	EN 60332-3-22 (Cat.A)
Acid Gases	EN 50267-1, EN 50267-2-2, EN 50267-2-3
Smoke Density	EN 61034-1, EN 61034-2



# Armada®

## Tight Buffered Distribution Fibre Optic Cable

### HFFR SHF-1

## Specification

Part Number	No. Of Fibres	Inner Jacket Ø [mm]	Oter Jacket Ø [mm]	Tensile Strength [N]	Weight [kg/km]
2410*044TB-01	4	5,50	8,47 ± 0,5	1000	-
2410*084TB-01	8	6,50	9,47 ± 0,5	1400	-
2410*124TB-01	12	7,30	10,27 ± 0,5	1600	-
2410*244TB-01	24	10,40	10,40 ± 0,5	2900	-

\* denotes fibre type requires ; 1=62.5/125 | 2 = 50/125 OM2 | 3 = 50/125 OM3 | 8 = 9/125

## Characteristics of Optical Fibre ITU-T G652D

Nominal MFD range at 1310 nm		8,6 - 9,4	µm
Nominal MFD range at 1550 nm		9,6 - 10,6	µm
Cladding diameter		125±0,7	µm
Coating diameter		245±10	µm
Core/cladding concentricity error		≤ 0,50	µm
Cladding non-circularity		≤ 0,70	%
Attenuation	1310 nm	≤ 0,36	dB/km
Attenuation	1383 nm	≤ 0,36	dB/km
Attenuation	1550 nm	≤ 0,23	dB/km
Attenuation	1285÷1330 nm	≤ 0,40	dB/km
Attenuation	1530÷1565 nm	≤ 0,25	dB/km
Attenuation	1565÷1625 nm	≤ 0,27	dB/km
Chromatic Dispersion coefficient	1285÷1330 nm	≤ 3,0	ps/nm • km average
Chromatic Dispersion coefficient	1285÷1330 nm	≤ 3,5	ps/nm • km maximum
Chromatic Dispersion coefficient	1550 nm	≤ 18	ps/nm • km
Chromatic Dispersion coefficient	1625 nm	≤ 22	ps/nm • km
Zero chromatic dispersion wavelength		1302 ≤ ≤ 1322	nm
Cut-off wavelength		≤ 1260	nm
Individual fibre polarization mode dispersion (PMD)		≤ 0,20	

# Armada®

## Tight Buffered Distribution Fibre Optic Cable

### HFFR SHF-1

## Characteristics Of Optical Fibre Multimode 62,5/125 IEC 60793-2-10 A1b

Core Diameter		62,5 ± 3	µm
Cladding Diameter		125 ± 2	µm
Coating Diameter		245 ± 10	µm
Core non-circularity		≤ 6	%
Cladding non-circularity		≤ 2	%
Numerical aperture		0,275 ± 0,015	
Attenuation	850 nm	≤ 3,5	dB/km
Attenuation	1300 nm	≤ 1,5	dB/km
Attenuation	850 nm	Min. 200	MHz • km
Attenuation	1300 nm	Min. 500	MHz • km

## Characteristics of Optical Fibre MULTIMODE 50/125 IEC 60793-2-10 TYPE A1a.1

Core diameter		50 ± 3	µm
Cladding diameter		125 ± 2	µm
Coating diameter		245±10	µm
Core non-circularity		≤ 6	%
Cladding non-circularity		≤ 2	%
Numerical aperture		0,2 ± 0,02	
Attenuation	850 nm	≤ 3	dB/km
Attenuation	1300 nm	≤ 0,8	dB/km
Bandwidth	850 nm	Min. 500	MHz • km
Bandwidth	1300 nm	Min. 500	MHz • km

*Belcom Cables Ltd. ("Belcom") reserves the right to make changes to the product described in this specification without prior notice. Belcom does not assume any liability which may occur due to the use of the specification described herein. Drawings are not to scale unless otherwise specified and are provided for general and informational purposes only. All values represented in this specification should be used as a guide only and exact product details can be confirmed at point of enquiry.*